



ARCHER RUBBER LLC
 213 CENTRAL STREET
 MILFORD, MA 01757-3458
 TEL: (508) 473-1870
 FAX: (508) 478-7078
www.archerrubber.com
sales@archerrubber.com

Engineered Coated Fabrics

STYLE# 13139

DESCRIPTION / CONSTRUCTION

Single Coated Hypalon on Polyester

AREAS OF APPLICATIONS

Static Dissipation

CHARACTERISTICS / PHYSICAL PROPERTIES

TEST / METHOD	Federal Standard 191A or ASTM	REQUIREMENT
Finish Color		Tan
Width (inches Trimmed)		60"
Weight (Oz./Sq. Yd.)	ASTM D3775	24.5 ± 2.5
Mullen Burst (PSI Min.)	ASTM D1424	350
Breaking Strength (1" Cut Strips)	ASTM D751	Warp 160 Fill 160
Breaking Strength (Grab Method)	ASTM D5035	Warp 275 Fill 275
Tear Strength (Tongue Method)	ASTM D5034	Warp 20.0 Fill 20.0
Taber Abrasion	ASTM D2261	4000 Cycles
Electrical Resistance	FED. SDT. 191A Method 5930	1 X 10 ⁸ Min. Ohms to 1 X 10 ¹⁰ Max. Ohms
1/8" Low-Temperature Bend Test	ASTM D2136	Pass

The information contained herein was developed in our laboratories and is believed reliable. It is offered in good faith. However, as prospective users conditions and methods of use are beyond our control, we recommend the user determine the suitability of this product before adapting our materials on a commercial scale.