



ARCHER RUBBER LLC
 213 CENTRAL STREET
 MILFORD, MA 01757-3458
 TEL: (508) 473-1870
 FAX: (508) 478-7078
www.archerrubber.com
sales@archerrubber.com

Engineered Coated Fabrics

STYLE# **12904**

DESCRIPTION / CONSTRUCTION

Single Coat FDA Neoprene on Knit

AREAS OF APPLICATIONS

Food Handling

CHARACTERISTICS / PHYSICAL PROPERTIES

TEST / METHOD	Federal Standard 191A or ASTM	REQUIREMENT
Finished Width (inches min. usable)		58
Finished Weight (Oz./Sq.Yd. min. to max.)	Method 5041	28.0 to 36.0
Finished Gauge (Inches)	Method ASTM D751	0.037 to 0.045
Breaking Strength (lbs. Min."2"width cut strip")	Method 5102	Warp 70 Fill 35
Elongation (% min.)	Method 5102	Warp 100% Fill 300%
Tear Strength (Grams min.)	Method 5132	Warp 300 Fill 3000
Coating Adhesion (lbs./2"Width)	Method 5970	4.5
Temperature range		-40° F to 180° F

The information contained herein was developed in our laboratories and is believed reliable. It is offered in good faith. However, as prospective users conditions and methods of use are beyond our control, we recommend the user determine the suitability of this product before adapting our materials on a commercial scale.