



ARCHER RUBBER LLC  
 213 CENTRAL STREET  
 MILFORD, MA 01757-3458  
 TEL: (508) 473-1870  
 FAX: (508) 478-7078  
[www.archerrubber.com](http://www.archerrubber.com)  
[sales@archerrubber.com](mailto:sales@archerrubber.com)

*Engineered Coated Fabrics*

STYLE# 13028

DESCRIPTION / CONSTRUCTION

*D/C Nitrile on Nylon Cured*

AREAS OF APPLICATIONS

*Mechanical Diaphragms & Gaskets*

CHARACTERISTICS / PHYSICAL PROPERTIES

TEST / METHOD	Federal Standard 191A or ASTM	REQUIREMENT
Finished Weight {Oz./Yd. <sup>2</sup> , min. to max.}	Fed. Std. 191A METHOD 5041	7.0 to 9.0
Finished Gauge {Inch min. to max.}	Fed. Std. 191A METHOD 5030	0.0055 to 0.0065
Finished Width {Inches minimum}		58
Mullen Burst {PSI Minimum}	Fed. Std. 191A METHOD 5122	100
Coating Adhesions {Lbs./inch minimum}	Fed. Std. 191A METHOD 5970	5.0
Breaking Strength {Lbs., min.}	Fed. Std. 191A METHOD 5100	Warp 50 Fill 50
Temperature Range		-40° F to 225° F

*The information contained herein was developed in our laboratories and is believed reliable. It is offered in good faith. However, as prospective users conditions and methods of use are beyond our control, we recommend the user determine the suitability of this product before adapting our materials on a commercial scale.*